## (19) FEDERAL REPUBLIC OF GERMANY GERMAN [Crest] PATENT OFFICE

(12)	UTILITY PATENT	U1
(11)	Register No.	G 94 14 868.6
(51)	Main class	A61K 49/04
	Subclass(es)	A61L 31/00
(22)	Filing date	September 13, 1994
(47)	Registration date	December 15, 1994
(43)	Publication in the Official Gazette	February 2, 1995
(54)	Title of invention	Particles for vascular embolization
(73)	Name and domicile of propri	etor  Klein, Hans-Martin, Dr.med., 52074 Aachen, DE; Günther, Rolf W., Prof. Dr.med., 52074 Aachen, DE
	LBE	Interest in licensing declared nonbindingly

Utility Patent, Prof. Dr. Günther/Dr. Klein

<u>September 9, 1994</u>

Title: Radiodense Embolisate Particles

**Description:** 

Vascular defects can lead to blood loss or improper blood distribution, with impairment of oxygen

supply. These defects can be occluded, "embolized," by the placement of wire coils, tissue adhesives,

balloons and synthetic particles.

To this end, after puncture of a vessel, usually in the inguinal region, a catheter is placed

immediately before the vascular defect. Through it embolisate is injected, resulting in the occlusion

of the vascular defect. A very important factor in the success of embolization is localization of the

embolisate by visualization on the radioscopic image. Correct placement is imperative to ensure the

success of the procedure; improper placement can result in injury.

Solid bodies such as metal coils are usually radiodense. Adhesives such as histoacrylic, for example,

are made radiodense by being mixed with contrast agent (e.g. lipiodol). The synthetic particles (e.g.

polyvinyl alcohol) that are often used to occlude small vascular branches, e.g. in vascular tumors,

cannot be localized in the x-ray image.

Object:

To enable synthetic particles (embolisate) to be visualized in the x-ray image by the admixture of

radiodense substances, e.g. iodine.

Advantages:

With the invention, synthetic particles are rendered visible in the radiographic image and control of

placement is ensured. This simplifies and increases the safety of angiographic embolization.

2

## Embodiment example:

- 1. Mixing a vinyl alcohol monomer solution with iodine-containing contrast agent in a concentration of 100 mg I/cm<sup>3</sup>
- 2. Polymerization
- 3. Comminuting the synthetic substance (milling)
- 4. Producing a quantity of particles of equal size (100, 250, 500, 1000  $\mu m)$

## **Protective Claim:**

 Particles for vascular embolization characterized in that they are doped with radiodense substances.